

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) Publication number:

0 174 128 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication of patent specification: 14.04.93 (51) Int. Cl.⁵: A61L 15/00, D21H 21/36

(21) Application number: 85305886.5

(22) Date of filing: 19.08.85

(54) Treated non-woven material.

(30) Priority: 31.08.84 GB 8422070

(43) Date of publication of application:
12.03.86 Bulletin 86/11

(45) Publication of the grant of the patent:
14.04.93 Bulletin 93/15

(84) Designated Contracting States:
AT BE CH DE FR GB IT LI LU NL SE


(56) References cited:
EP-A- 0 099 209
EP-A- 0 136 900
US-A- 4 311 479

CHEMICAL ABSTRACTS, vol. 102, no. 18, 6th
May 1985, page 76, abstract no. 150882c,
Columbus, Ohio, US

(73) Proprietor: IMPERIAL CHEMICAL INDUSTRIES
PLC
Imperial Chemical House, Millbank
London SW1P 3JF(GB)

(72) Inventor: Fawkes, David Melville
40 Beacon View
Marble, Cheshire(GB)

(74) Representative: Pugsley, Roger Graham et al
ICI Group Patents Services Dept. PO Box 6
Shire Park Bessemer Road
Welwyn Garden City Herts, AL7 1HD (GB)



Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid (Art. 99(1) European patent convention).

Description


This specification describes a treated non-woven material which is resistant to the activity of microbial species, especially bacteria, and a process for the preparation of such material.

5 It is well known that the generation of noxious malodours, especially the more pungent ammoniacal
odours in disposable nappies and the like is caused by the action of micro-organisms on the retained body
fluids. This microbiological activity can also result in various skin rashes. Several attempts have been made
to control such odours by treating the disposable nappy with a biocide for example chlorhexidine as
described in UK 1443086 and a quaternary ammonium compound as described in American Dyestuff
10 Reporter, June 1984, pages 35 to 45. None, however, have found commercial acceptance.

It is also known to apply polymeric biguanides to the non-woven materials to be used as wipes for transferring the biocide to a solid surface to be disinfected. Such methods have been described, for example, in US 4311479 and EP 99209. These materials, however, are not designed to retain the biocide and are consequently not adapted to prevent microbiological activity within the non-woven material.

15 It has now been found that polymeric biguanides can be absorbed onto the non-woven materials commonly used in the manufacture of disposable nappies and the like, and that such treated material inhibits the growth of those micro-organisms which give rise to the afore-mentioned malodours and skin rashes.

Thus, according to the present invention there is provided an article which is a disposable nappy, a 20 disposable feminine hygiene pad or an incontinence pad, and which is formed from a non-woven material treated with a linear polymeric biguanide in which the recurring unit is of the formula:




wherein X and Y, which may be the same or different, represent bridging groups in which the total number of carbon atoms in X and Y taken together, directly interposed between the pairs of nitrogen atoms linked thereby, is from 10 to 16, or the salt thereof with an acid.

The bridging groups X and Y, which may be the same or different, preferably comprise polymethylene chains, optionally interrupted by oxygen, nitrogen or sulphur atoms and may incorporate saturated or unsaturated cyclic groups. When the groups X and Y incorporate cyclic groups, the number of carbon atoms directly interposed between pairs of nitrogen atoms includes the carbon atoms in the shortest segment of the cyclic group.

In a preferred polymeric biguanide, X and Y are both polymethylene groups containing from 3 to 12 carbon atoms and more preferably X and Y are both hexamethylene. The polymeric biguanide preferably has a molecular weight in the range 500 to 20,000 and contains from 5 to 12 biguanide units.

Especially preferred is a mixture of polymeric biguanides of the formula:



wherein n varies from about 6 to 10, having a number average molecular weight from about 1300 to 2200, preferably in the form of salts with hydrochloric acid.

45 The polymeric biguanide has broad spectrum of activity, at very low levels, against bacteria, fungi and yeasts, particularly those associated with the human body. Furthermore, it harmless to macrobiotic systems and, in particular, is not a skin sensitiser. It will, therefore, not give rise to problems when applied to articles which will be in direct contact with the skin for extended periods

The article is suitable for the collection of human body emissions, generally fluid emissions, such as urine, and excreta, which are susceptible to bacterial degradation. When such emissions are in contact with bacteria for an extended period, the bacteria can cause changes in the emissions, and chemical substances therein, which can have deleterious effects on the environment, i.e. the body with which the non-woven material is in contact or the surrounding atmosphere. Thus, when disposable nappies become contaminated with urine bacteria present in the anal region effect chemical reactions in the urine which raise the pH and lead to the formation of malodorous chemicals; one product of bacterial activity in urine is the formation of ammonia. Extended contact of the degradation products with the skin can lead to "nappy rash" and general discomfort to the wearer.

Various attempts have been made to control odours and 'nappy rashes' by incorporating a biocide into disposable nappies (e.g. DC 5700, American Dyestuff Reporter, June 1984, p.35-45, and chlorhexidine as described in UK 1443086, 23.2.73. assigned to Proctor & Gamble) but none have found commercial acceptance.

It has now been found that non-woven materials treated with the polymeric biguanide are particularly suitable for use in the preparation of such articles because of the significant inhibition of bacterial activity when the article becomes contaminated with body emissions.

In addition to protection against bacterial activity in the body emissions absorbed on the material, the polymeric biguanide will also provide protection of the non-woven material itself against bacterial action during storage prior to use.

The non-woven material preferably contains from 100 ppm up to 100,000 ppm, and more preferably from 500 ppm up to 5000 ppm, of the polymeric biguanide.

The non-woven material may be treated with the polymeric biguanide during the preparation of the material by, so example, soaking the constituent fibres in a solution of the polymeric biguanide or spraying the material after formation with a solution thereof. As the polymeric biguanide is readily soluble in water an aqueous solution may be used.

The polymeric biguanide has a strong affinity for cellulosic, and related synthetic, materials which are conventionally used for the preparation of the present articles, and it is very efficiently taken up by such materials from an aqueous solution. The polymeric biguanide, in the form of its hydrochloride salt, is extremely soluble in water and aqueous solutions thereof are substantially non-foaming.

Since, the absorbent wadding or cellulosic material of the present articles is the major structural component responsible for absorbing body fluids such as urine, this is the most logical place to locate the bioactive compound. In order that additional drying costs are avoided, such application should preferably take place from aqueous media during pre-existing wet processing stages during manufacture. In order to ensure uniform uptake of the biocide, such processes involve high speed agitation of the cellulose fibres in aqueous dispersion. In such a process, the water soluble polymeric biguanide is particularly well suited since it is substantially non-foaming. In this respect it is superior to the chlorhexidine cited in UK 1443086 which foams to a greater extent and also produces a more stable foam. Furthermore, the use of ethanolic solutions of chlorhexidine disclosed and exemplified in UK 1443086 constitute an unacceptable industrial hazard compared with the use of aqueous solutions of the polymeric biguanide. Additionally, chlorhexidine must be protected from light which is not required in the case of the polymeric biguanide, and application of the latter to the appropriate support media leads to no discolouration.

When chlorhexidine and the polymeric biguanide are applied to cellulosic substrates, they exhibit similar activity to bacteria such as *Pr. vulgaris*, although the polymeric biguanide surprisingly shows greater activity against the clinically important *Ps. aeruginosa*.

Quaternary ammonium compounds have also been proposed for use in disposable non-woven materials to suppress odours and control micro-organisms. Generally, they suffer from pronounced foaming deficiencies and lack of substantivity leading to problems during application. They are also not particularly effective in controlling micro organisms in this particular application. This is especially true in the case of the reactive silicon based quaternary ammonium compound, commercially available as DC 5700 from Dow-Corning which has recently been recommended for such outlets (cf. American Dyestuffs Reporter, June 1984, p.35-45).

Various techniques have been proposed in the past for assessing body odours, and most have resorted to nasal assessment using panels of experts, e.g. odour control in mens socks using DC 5700 ref "A new durable Antimicrobial Finish for Textiles", R.L.Getting and B.L.Triplett, paper presented at the AATCC National Conference 1978, and more recently the use of polymeric biguanides in deodorant formulations claimed in US 4478821 assigned to Gillette. These methods are not particularly sophisticated. In the American Dyestuff Reporter, June 1984, p.35-45, odour assessment based on the ureolytic activity of *Proteus mirabilis* and measurement of ammonia in the free-air space is described. This approach whilst being an improvement on the "nasal panel" methodology, lacks refinement and sensitivity, being dependent on pH and the buffering capacity of urine. Consequently, we have developed this approach further to enable the total ammonia content to be accurately measured, even from the earliest stage of bacterial ureolytic activity when all the ammonia generated is bound as inorganic and/or organic-salts, and does not manifest itself in the free space above such liquids. This method is based on first determining the ureolytic activity of those micro organisms implicated in odour generation using the technique outlined below.

0.5ml nutrient broth into which individual micro organisms had been repeatedly subcultured (containing approximately 10^8 cfu/ml) was added to 9.5ml synthetic urine devoid of ammonium ion. 1ml of this inoculated urine was entered into a sterile closed vial and incubated at 36° C. The ammonia generated was

determined after 6 hours and 24 hours by dilution with 9ml 0.02N hydrochloric acid followed by millipore filtration, and the ammonium ion content determined by column chromatography using a Dionex chromatographic analyser. The ammonia content found in the samples is listed below (in ppm).

		6 hrs	24 hrs
Entero bacteria	Klebsiella pneumoniae	36	420
	Escherichia coli	28	100
	Proteus vulgaris	500	1290
Gram positive cocci	Staphylococcus aureus	6	280
	Streptococcus faecalis	3	74
Anaerobes	Lacto bacillus sp.	3	50
Pseudomonads	Pseudomonas aeruginosa 1	1200	2220
	Pseudomonas aeruginosa 2	78	460
	Pseudomonas aeruginosa 3	34	380
	Pseudomonas aeruginosa 4	28	290
Yeast	Endomycopsis (formerly Candida) albicans	0	24

The invention is further illustrated by the following Examples in which all parts and percentages are by weight unless otherwise indicated.

Example 1

The absorbent wadding material was stripped from an adult incontinence pad and 2.5 parts dispersed in 200 parts water by rapid agitation. Sufficient quantities of a 20% aqueous solution of a mixture of polyhexamethylene biguanide dihydrochlorides (PHMB), having number average molecular weights from 1300-2200, were added, at neutral pH, to separate samples of the absorbent wadding, to give 100, 500, 1000 and 3000 ppm of PHMB on the substrate. The PHMB was completely adsorbed. A control sample contained no PHMB but was otherwise treated as the test samples. Each sample was then cast into a paper sheet measuring approximately 7" x 5", and dried on a steam heated calender drum.

Two 1" squares of each sheet were placed in a sterile petri dish and wetted with 1 part synthetic urine (pH 6.6). The wetted sheet was then inoculated with the gram-negative, ureolytic bacterium, *Proteus vulgaris* (ca 10^6 cFu), and incubated at 37°C. Generation of ammonia was followed by monitoring the changes in pH. After 24 and 48 hours, the sheet derived from the sample impregnated with 1000 ppm PHMB showed no change of pH whereas the sheet derived from the control exhibited a marked increase in pH associated with the characteristic smell of ammonia.

Example 2

When the *Proteus vulgaris* used in Example 1 was replaced by a wild bacterium isolated and cultured from a soiled infant's nappy, substantially similar results were obtained.

Example 3

Absorbent paper exhibiting similar grammage (ca 100gm/m²) to the sheets cast from wadding material described in Example 1 was passed through aqueous solutions of PHMB at various concentrations, squeezed and dried on a hot calender drum to give the following concentrations of PHMB on the absorbent papers (cf. table below).

0.5g of the above papers were entered into a sterile closed vial and impregnated with 1ml inoculated synthetic urine prepared by adding 0.5ml broth culture of *Proteus vulgaris* to 9.5ml urine. After incubation at 36°C, samples were removed at various times, and the ammonia generated determined by extraction into 9ml 0.02N hydrochloric acid, and millipore filtered. The ammonia content was determined by chromatographic analysis and gave the following results expressed in ppm ammonia.

Concn. PHMB applied (ppm)	Incubation (hours)					
	1	2	4	6	8	24
0	53	86	307	442	594	1564
125	32	61	224	446	400	640
250	30	42	64	147	210	133
500	20	25	36	40	30	119
1000	20	-	-	-	20	53
2000	20	-	-	-	20	40
3000	20	-	-	-	20	89

Example 4

Absorbent papers containing 1000 ppm PHMB prepared as above were challenged with various micro organisms including a cocktail prepared by mixing equal parts of all eleven organisms. Incubation and analysis was carried out as described in Example 3 and gave the following results.

Concn. PHMB applied (ppm)	Incubation (hours)							Challenging organism
	2	4	6	8	13	18	24	
0	211	605	1190	1410	1860	2000	1870	Ps.aeruginosa 1
1000	27	32	47	44	120	56	76	Ps.aeruginosa 1
"			15				23	E.coli
"			17				18	S.faecalis
"			18				14	Lacto bacillus
"			18				35	P.vulgaris
"			21				24	St.aureus
"			14				16	K.pneumoniae
"			8				10	E.albicans
"			26				36	Ps.aeruginosa 2
"			26				34	Ps.aeruginosa 3
"			18				33	Ps.aeruginosa 4
0	43	410	590	740	1110	1200	1400	Cocktail
1000	17	39	22	27	29	24	27	Cocktail

Example 5

Example 4 was repeated except that the 0.5g substrate was impregnated with 1.66ml inoculated urine in place of the 1ml used in Example 3, giving the following results.

Concn. PHMB applied (ppm)	Incubation (hours)							Challenging organism
	2	4	6	8	13	18	24	
0	280	840	1200	2040	2500	2770	2700	Ps.aeruginosa 1
1000	65	110	230	110	83	119	156	Ps.aeruginosa 1
0	37	151	366	874	1300	1390	1480	Cocktail
1000	16	17	19	17	21	45	35	Cocktail
1000	23	24	23	18	19	17	22	St.aureus
1000	12	10	13	10	15	19	21	K.pneumoniae

Example 6

10g wadding was stripped from a commercially available disposable nappy and dispersed in 800ml water by rapid agitation. An aqueous solution of PHMB was added to give 1000 ppm and 1500 ppm PHMB on weight of substrate. The PHMB was rapidly and completely absorbed. Water was removed from the treated wadding by filtration and rotary evaporation, and the wadding "fluffed" by high speed air agitation. The wadding so obtained exhibited no discolouration, with excellent absorbency.

0.5g samples of the treated wadding was entered into a closed sterile vial and impregnated with 1ml inoculated synthetic urine, and analysed as in the foregoing examples to give the following results. Ammonia content expressed in ppm.

Concn. PHMB applied (ppm)	Incubation (hours)							Challenging organism
	2	4	6	8	13	18	24	
0	208	662	1272	1432	1542	1602	1522	Pr.vulgaris
1000	8	48	143	311	348	298	346	Pr.vulgaris
1500	0	0	0	10	22	86	135	Pr.vulgaris
0	22	270	732	1042	1122	1072	1212	Cocktail of 11 micro organisms
1000	0	0	152	330	418	446	378	
1500	0	0	0	27	21	72	52	

In the above example, as in the foregoing examples, the untreated substrate when contacted with urine containing a micro organism rapidly acquired an objectional urinal odour which becomes increasingly noticeable after 8 hours incubation. This is especially true when challenged with the cocktail of micro organisms.

The treated substrate containing PHMB remains completely free from such odours even after 24 hours and exhibits the freshness of damp domestic washing.

Example 7

The absorbent paper containing 1000 ppm PHMB, following challenge with *Pr.vulgaris* and synthetic urine and incubated for 24 hours was pressed onto a nutrient agar plate, and the plate incubated overnight at 37° C. The plate displayed no microbial growth. A similar paper containing no PHMB when treated in the same manner resulted in heavy growth of the micro organism.

Example 8

Absorbent papers (grammage 102gm/m²) were impregnated with PHMB and chlorhexidine by padding through the appropriate aqueous concentration of the bio-active compound, squeezing between mangles to give 120% liquor retention and dried on a heated calender drum. The aqueous solutions of biocide were calculated to give 1000 ppm of PHMB and chlorhexidine on the support.

0.5g support were folded and placed in a sealed sterile vial, and challenged with 1ml synthetic urine made by adding 0.5ml overnight broth culture of *Ps.aeruginosa* to 9.5ml synthetic urine. After incubation at 36° C, the ammonia generated was extracted into 9ml 0.02N hydrochloric acid, millipore filtered and analysed. The results are tabulated below in ppm ammonia.

Biocide added (ppm)	Incubation (hours)						
	2	4	6	8	13	18	24
0	21	20	62	104	200	305	386
1000 ppm PHMB	21	17	19	29	24	29	27
1000 ppm chlorhexidine	NA	NA	NA	NA	19	26	280
1000 ppm Arquad 18	15	20	60	118	221	352	433
3000 ppm DC 5700	15	18	51	113	240	373	418
NA - not available.							
Arquad 18 is the octadecyl trimethyl ammonium chloride supplied by Armour Chemical Division.							
DC 5700 is trimethoxy silyl propyl octadecyl dimethyl ammonium chloride, sold by Dow Corning.							

Example 9

Papers were prepared by taking wadding material stripped from a commercially available disposable nappy (2.5g) and dispersing in 200ml water by rapid agitation. 5.0ml of 0.05% aqueous solution of PHMB and chlorhexidine were added respectively, stirred for a further 5 minutes, and the treated pulp cast into a hand sheet by discharging onto a wire screen, pressing to express surplus water and drying on a hot calender drum. 0.5g of the paper (90g/m²) so obtained were treated as in Example 8 to give the following results.

Biocide added (ppm)	Incubation (hours)			
	2	4	8	24
1000 ppm PHMB	45	38	38	102
1000 ppm chlorhexidine	33	30	87	327

Example 10

Absorbent paper (ca. 100g/m²) was impregnated by padding and squeezing to give the following uptake of bio-active compound as listed below. 0.5g of the treated papers were challenged with 1ml synthetic urine containing *Pr.vulgaris* in place of the *Ps.aeruginosa* used in Example 8, otherwise the conditions and analysis were similar to those described in Example 8. The ammonia generated is as listed in the table.

Biocide added (ppm)	Incubation (hours)						
	2	4	6	8	13	18	24
0	49	82	170	184	520	580	700
1000 ppm PHMB	27	28	33	33	60	62	75
2000 ppm chlorhexidine	19	24	26	23	38	63	52
1000 ppm Arquad 18	18	26	29	31	68	66	88
3000 ppm DC 5700	34	47	60	77	150	210	200

Example 11

A disposable nappy was sprayed with an aqueous solution of PHMB such as to produce a loading of 1000 ppm PHMB relative to the weight of wadding. After drying, a 0.5g sample comprising "fluffed" wadding and cover stock material was evaluated in a similar manner to that described in Example 4. When challenged with *Ps.aeruginosa* and a cocktail of 11 organisms, it exhibited similar results. As in previous examples, the material treated with PHMB when challenged with either the single organism or the cocktail produced no objectionable odours even after 24 hours incubation, whereas the untreated substrate when so

treated yield the expected objectionable urinal odours even after 8 hours incubation.


Example 12

A commercially available incontinence pad whose construction comprised a plastic backing, coverstock and creped paper as absorbent medium was impregnated with PHMB by padding through an aqueous solution of the biocide followed by squeezing and drying on a hot calender. The biocide retained was 1000 ppm PHMB.

0.5g of this material was treated as described in Example 4, and gave similar results.


Claims

1. An article which is a disposable nappy, a disposable feminine hygiene pad or an incontinence pad, and which is formed from a non-woven material treated with a linear polymeric biguanide in which the recurring unit is of the formula:



wherein X and Y, which may be the same or different, represent bridging groups in which the total number of carbon atoms in X and Y taken together, directly interposed between the pairs of nitrogen atoms linked thereby, is from 10 to 16, or the salt thereof with an acid.

2. An article according to claim 1 which contains absorbent wadding which has been treated with the linear polymeric biguanide.
3. An article according to either claim 1 or claim 2 wherein the groups X and Y are polymethylene groups containing from 3 to 12 carbon atoms.
4. An article according to any one of claims 1 to 3 wherein X and Y are hexamethylene groups.
5. An article according to any one of claims 1 to 4 wherein the polymeric biguanide has a molecular weight in the range 500 to 20,000.
6. An article according to any one of claims 1 to 5 wherein the polymeric biguanide contains from 5 to 12 biguanide units.
7. An article according to any one of claims 1 to 6 wherein the polymeric biguanide is present at a concentration ranging from 500 to 5000 ppm.
8. An article according to any one of claims 1 to 7 wherein the polymeric biguanide is a mixture of polyhexamethylene biguanide dihydrochlorides having number average molecular weights from 1300-2200.
9. The use of an article formed from a non-woven material treated with a linear polymeric biguanide for the collection of human body emissions wherein the linear polymeric biguanide is one in which the recurring unit is of the formula:



wherein X and Y, which may be the same or different, represent bridging groups in which the total number of carbon atoms in X and Y taken together, directly interposed between the pairs of nitrogen atoms linked thereby, is from 10 to 16, or the salt thereof with an acid.


- 5 10. The use of an article according to claim 9 as a disposable nappy, a disposable feminine hygiene pad or an incontinence pad.
11. The use of an article according to claim 10 wherein the non-woven material is absorbent wadding which has been treated with the linear polymeric biguanide.

10

Patentansprüche

1. Gegenstand, bei welchem es sich um eine Einmalwindel, eine hygienische Einmaldamenbinde oder ein Einmalinkontinenzkissen handelt und welcher aus einem nichtgewebten Stoffmaterial besteht, das mit einem linearen polymeren Biguanid, in welchem die Wiederholungseinheit die Formel


15



25 besitzt, worin X und Y, welche gleich oder verschieden sein können, für Brückengruppen stehen, wobei die Gesamtzahl der Kohlenstoffatome in X und Y, die sich direkt zwischen den angrenzenden Paaren von Stickstoffatomen befinden, 10 bis 16 beträgt, oder mit einem Salz desselben, das mit einer Säure gebildet ist, behandelt worden ist.

2. Gegenstand nach Anspruch 1, welcher ein absorbierendes Kissen enthält, das mit dem linearen polymeren Biguanid behandelt worden ist.
3. Gegenstand nach Anspruch 1 oder 2, bei welchem die Gruppen X und Y Polymethylen-Gruppen mit 3 bis 12 Kohlenstoffatomen sind.
- 35 4. Gegenstand nach einem der Ansprüche 1 bis 3, bei welchem X und Y für Hexamethylen-Gruppen stehen.
5. Gegenstand nach einem der Ansprüche 1 bis 4, bei welchem das polymere Biguanid ein Molekulargewicht im Bereich von 500 bis 20 000 aufweist.
- 40 6. Gegenstand nach einem der Ansprüche 1 bis 5, bei welchem das polymere Biguanid 5 bis 12 Biguanid-Einheiten enthält.
7. Gegenstand nach einem der Ansprüche 1 bis 6, bei welchem das polymere Biguanid in einer Konzentration im Bereich von 500 bis 5000 ppm vorliegt.
- 45 8. Gegenstand nach einem der Ansprüche 1 bis 7, bei welchem das polymere Biguanid ein Gemisch von Polyhexamethylenbiguanid-dihydrochloriden mit einem zahlenmäßigen Durchschnittsmolekulargewicht von 1300 bis 2200 ist.
- 50 9. Die Verwendung eines Gegenstands, der aus einem mit einem linearen polymeren Biguanid behandelten nichtgewebten Stoffmaterial hergestellt ist, zur Aufnahme von menschlichen Körperabsonderungen, bei welchem das lineare polymere Biguanid aus einem solchen, in welchem die Wiederholungseinheit die Formel

55



5

10 besitzt, worin X und Y, welche gleich oder verschieden sein können, für Brückengruppen stehen, wobei die Gesamtzahl der Kohlenstoffatome in X und Y, die sich direkt zwischen den angrenzenden Paaren von Stickstoffatomen befinden, 10 bis 16 beträgt, oder aus einem Salz desselben, das mit einer Säure gebildet ist, besteht.

10. Die Verwendung eines Gegenstands nach Anspruch 9 als Einmalwindel, hygienische Einmaldamenbinde oder Einmalinkontinenzkissen.


15

11. Die Verwendung eines Gegenstands nach Anspruch 10, bei welchem das nichtgewebte Stoffmaterial aus einem absorbierenden Kissen besteht, das mit dem linearen polymeren Biguanid behandelt worden ist.

20 Revendications

1. Produit manufacturé qui est une couche jetable, une protection d'hygiène féminine jetable ou une protection pour incontinent, qui est formé à partir d'une matière non tissée traitée à l'aide d'un biguanide polymère linéaire dans lequel l'unité récurrente est de la formule :

25



30

(I)

35

où

X et Y, qui peuvent être identiques ou différents, représentent des radicaux de pontage dans lesquels le nombre total d'atomes de carbone dans X et Y pris ensemble, interposés directement entre les paires d'atomes d'azote ainsi unis, est de 10 à 16,

40

ou du sel de celui-ci avec un acide.

2. Produit manufacturé suivant la revendication 1, qui contient un rembourrage absorbant qui a été traité à l'aide du biguanide polymère linéaire.

45

3. Produit manufacturé suivant la revendication 1 ou 2, dans lequel les radicaux X et Y sont des radicaux polyméthylène comptant 3 à 12 atomes de carbone.

4. Produit manufacturé suivant l'une quelconque des revendications 1 à 3, dans lequel X et Y sont des radicaux hexaméthylène.

50


5. Produit manufacturé suivant l'une quelconque des revendications 1 à 4, dans lequel le biguanide polymère a un poids moléculaire de l'intervalle de 500 à 20 000.

55

6. Produit manufacturé suivant l'une quelconque des revendications 1 à 5, dans lequel le biguanide polymère contient 5 à 12 unités biguanide.

7. Produit manufacturé suivant l'une quelconque des revendications 1 à 6, dans lequel le biguanide polymère est présent en une concentration s'échelonnant de 500 à 5000 ppm.

8. Produit manufacturé suivant l'une quelconque des revendications 1 à 7, dans lequel le biguanide polymère est un mélange de dichlorhydrates de polyhexaméthylène biguanide ayant des poids moléculaires moyens en nombre de 1300 à 2200.
9. Utilisation d'un produit manufacturé formé d'une matière non tissée traitée à l'aide d'un biguanide polymère linéaire pour la collecte des excréments du corps humain, dans laquelle le biguanide polymère linéaire est un biguanide dans lequel l'unité récurrente est de la formule :



15

(I)

où

- 20 X et Y, qui peuvent être identiques ou différents, représentent des radicaux de pontage dans lesquels le nombre total d'atomes de carbone dans X et Y pris ensemble, interposés directement entre les paires d'atomes d'azote ainsi unis, est de 10 à 16,
ou du sel de celui-ci avec un acide.

- 25 10. Utilisation d'un produit manufacturé suivant la revendication 9, comme couche jetable, protection d'hygiène féminine jetable ou protection pour incontinent.
- 30 11. Utilisation d'un produit manufacturé suivant la revendication 10, dans laquelle la matière non tissée est un rembourrage absorbant qui a été traité à l'aide du biguanide polymère linéaire.

35

40

45

50

55

60